Summit Architectural
Complete plywood and panel solutions

CONSTRUCTION

H3 Construction Ply

CHARACTERISTICS

Construction H3 CCA Radiata Tanalised has a H3.2 CCA treatment for high durability in exterior or wet area situations. However the more modern ACQ treatment system is available on request. H3 CCA ply is particularly popular in many roofing systems as a structural substrate.

USES

Flooring, Bracing
Wall Linings.
Shelving and temporary walls.
Formwork and general construction.
Sub Linings

SPECIFICATIONS

Sheet Size	Sheet Thickness	Weight	Grading
2400x1200	7mm, 9mm, 12mm, 15mm, 18mm	Ave 500kg/m3	CD or DD
(2700 on request)	(or 17mm & 19mm options), 21mm,		CD CPD or DD
	25mm, 30mm		CD
2700x1200 TG	15mm, 17mm, 19mm, 21mm		Floor TG
3000x1200	15mm, 17mm, 19mm, 21mm		CD
3000x1200 TG	15mm, 17mm, 19mm, 21mm		Floor TG

Material and Colour	Pinus Radiata, Creamy yellow, fine grain / Treated to CCA H3.2
Texture	Fine grain, rotary cut
Glue Bond	A-Bond, Super E-Zero on request
Origin	NZ and Chile
Environmental	Plantation Grown PEFC or FSC on request

HANDLING & APPLICATION INFORMATION

CD grade while generally having a nice face is considered a paint grade product not a stain grade. Summit has both structural and non-structural options, but unless specifically requested non-structural will be supplied. Not guaranteed in direct weather application.
Plywood is a natural product that can be affected by changes in weather conditions: moisture and temperature. Increased moisture content temperature variation may cause internal stresses causing previously flat sheets to bow.
At Summitply, precautions are taken to minimize this effect. However, once the plywood has left our warehouse we cannot guarantee sheets to remain flat unless fastened.
When storing panels, stack on a firm raised base with enough support to prevent sagging. Cover the pallet to protect top and edges.

For further information, contact our dedicated, trained sales staff.
North Island 06 344 1126
Christchurch 03 928 1520

Freephone 0800 344 112
E sales@summitply.co.nz **F** 06 344 1129
www.summitply.co.nz